


# **TECHNICAL DATASHEET**

PLAKA - STRUKTOPLAN Structural formwork panel for concrete REF 04.16.04 - Version V01 - 12/08/2020



Page 1 of 2



### Description



Structural formwork panel for concrete.

### **Application fields**

Struktoplan is suitable for (des voiles in structural concrete ?), plate type of 10 cm wide, with uniformity and stability.

A large number of multiple uses and reuses are possible while ensuring a consistent appearance.

#### **Properties**

Mechanical properties					
Large formwork panel in accordance					
with the norm:	DIN 68792				
Surfaces :	2-coated faces of reinforced phenolic resin (app. 470 g/m <sup>2</sup> );				
	1 side view wood structure imitation about 100 mm wide, other				
	side is smooth.				
Structure:	Peeled veneers of exotic wood.				
Collage:	BFU 100 DIN 68705.				
Elasticity module E (N/mm <sup>2</sup> )	Longitudinale : 7300				
	Transversale : 2700				
Tensile strength (N/mm <sup>2</sup> )	Longitudinale : 94				
	Transversale : 47				

Subject to change.

Attention: indicative values, no feature/tolerance can be guaranteed in accordance with DIN 68791.

©Copyright protected

This sheet, written with great care, supersedes all previous versions. The technical information on the design, models, illustrations, design values and specifications are believed to be accurate. We make no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with non suitable use of this product. We reserve the right to modify the contents of this form without prior notice.

For further information, please contact your Leviat office. Belgium : <u>info.plaka.be@leviat.com</u> / + 32 (0) 2 582 29 45 France : <u>info.plaka.fr@leviat.com</u> / +33 (0) 5 34 25 54 82




# **TECHNICAL DATASHEET**

# **PLAKA - STRUKTOPLAN**

Structural formwork panel for concrete REF 04.16.04 - Version V01 - 12/08/2020



Page 2 of 2



### Performance

The formworks must be sealed to avoid concrete nuances due to loss of dust.

The surface must be perfectly clean and dry, if necessary, use an oil separator.

The panels must be well maintained: nailed, glued with glue or double sided tape.

They must be in perfect contact with the surface.

The panels receive a layer of concrete release agent specifically for structural concrete (Trennfit Super) before each concrete casting, after removing all traces of dirt.

The implementation of the concrete must be of malleable structure, the doses must continue rigorously constant.

Reversals are not permissible.

Use is made of a filler tube at high formwork.

The concrete is shaken regularly.

Material dimensions								
Code	Scheme	Article	W x L (mm)	T (mm)	m²/Box	Weight (kg/m²)		
WES04		STRUKTOPLAN	1200 x 3000(*)	5,5	3,60	4,0		

## Dimensions

(\*) Direction of the structure

#### Storage

Panels should be stored horizontally and protected from UV rays.

©Copyright protected

This sheet, written with great care, supersedes all previous versions. The technical information on the design, models, illustrations, design values and specifications are believed to be accurate. We make no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with non suitable use of this product. We reserve the right to modify the contents of this form without prior notice.

For further information, please contact your Leviat office. Belgium : <u>info.plaka.be@leviat.com</u> / + 32 (0) 2 582 29 45 France : <u>info.plaka.fr@leviat.com</u> / +33 (0) 5 34 25 54 82